

HYPERDESMO®-ADY 500

One component, non-yellowing, elastic, polyurethane topcoat for waterproofing & protection.

DESCRIPTION

HYPERDESMO®-ADY 500 is a fully aliphatic, one component, polyurethane fluid. Upon curing, it produces a tough but highly elastic non-yellowing membrane. It contains pigments and special inorganic fillers that result in excellent mechanical, chemical, thermal, UV and natural element resistance properties.

It is used as a top-coat to the **HYPERDESMO® System**, offering increased UV resistance and colour protection.

HYPERDESMO®-ADY 500 does NOT yellow or wear out when exposed directly to sunlight (it is aliphatic) even in dark colours, e.g. red.

Apply using brush, roller or airless spraying. Consumption: 0.2-0.5 kg/m².

RECOMMENDED FOR

Top-coating of the **HYPERDESMO® System** for colour protection and long-term solar reflectance.

FEATURES & BENEFITS

- Excellent weather and UV resistance, no yellowing (it is fully aliphatic).
- Excellent mechanical properties, high elasticity, tensile and tear strength.
- Highly hydrophobic.
- Excellent chemical and hydrolysis resistance.

APPLICATION PROCEDURE

Mixing:

Use a low speed (300 rpm) mixer. Add SOLVENT-01 5-10% for application by spraying.

Application:

By brush, roller or airless spraying, within 72 hours of application of the main membrane.

CONSUMPTION

0.2-0.5 kg/m².

CLEANING

Clean tools and equipment first with paper towels and then using SOLVENT-01. Rollers will not be re-usable.

PACKAGING

1 kg, 5 kg and 15 kg drums.

SHELF LIFE

Can be kept for minimum 12 months in the original unopened pails in dry places and at temperatures of 5-25 °C. Once a pail has been opened, use as soon as possible.

SAFETY INFORMATION

Contains volatile flammable solvents. Apply in well-ventilated, no smoking areas, away from naked flames. In closed spaces use ventilators and carbon active masks. Keep in mind that solvents are heavier than air so they creep on the floor. The MSDS (Material Safety Data Sheet) is available on request.

HYPERDESMO[®]-ADY 500

TECHNICAL SPECIFICATIONS

PROPERTY	UNITS	METHOD	SPECIFICATION
Viscosity (BROOKFIELD)	cP	ASTM D2196-86, @ 25 °C	100-500
Density @ 20 °C	gr/cm ³	ASTM D1475 / DIN 53217 / ISO 2811	1.15-1.25
Hardness	Shore A	ASTM D2240	75
Tensile strength	Kg/cm ² (N/mm ²)	ASTM D412	100 (10)
Percent elongation	%	ASTM D412	> 500
Thermal resistance (100 days @ 80 °C)	-	EOTA TR011	passed
QUV Accelerated Weathering Test	-	ASTM G53	passed (2000 hours)

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA S.A. BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. ALCHIMICA S.A. RESERVES THE RIGHT TO CHANGE AT ANY TIME THE PROPERTIES OF ITS PRODUCTS. PLEASE REFER TO THE CURRENT VERSION OF THE TECHNICAL DATA SHEET, AVAILABLE FROM OUR WEB SITE WWW.ALCHIMICA.COM

