

AQUASMART®-DUR

Product Data Sheet

Two-component, Low Viscosity, Water Based, 1:1 By Volume, Epoxy Coating /Primer.

Description

AQUASMART®-DUR is a revolutionary epoxy based primer/coating formulated by **ALCHIMICA®** research and development laboratory. It is a two-component, water based, epoxy coating, specially formulated for use in a 1:1 by volume ratio. This allows the user to consume even the smallest quantities and store the material for future needs. The viscosity of the material is low and the pot life long, making it ideal for DIY applications.

AQUASMART®-DUR can be easily colored with universal pigment pastes available in hardware stores and can be filled with equal parts of quartz sand giving rise to an excellent protective coating for concrete surfaces. The material displays very low levels of yellowing upon prolonged exposure to UV.

Recommended For

- Primer for **AQUASMART®**, **HYPERDESMO®** and Epoxy range of products.
- Primer when humidity barrier properties are required and Sealing coat for concrete
- Adhesive layer between old and new concrete
- Anti-Dust floor coating and protective coating for old metal based structures

Compliance

- The adhesion strength of **AQUASMART®-DUR** exceeds the requirements of EOTA (European Organization of Technical Approval).
- **CE** certified according EN 1504-2:2004.

Features & Benefits

- 1:1 By volume application ratio
- Quick curing even at lower temperatures
- Low-odor, safe and non-flammable (zero VOC)
- Suitable for application in closed spaces
- Easy clean up
- Strong adhesion even on damp or green concrete. Also on iron, galvanized steel, aluminium, glass and wood
- Good mechanical properties and abrasion resistance
- Easy coloring with water based pigment paste
- Visible pot-life

Application Procedure

- ✓ **Mixing:** Mix the two components well manually or using a low speed (300 rpm) mixer.
- ✓ **As primer** – Application in thin coats only. Apply with roller in one or two coats with total maximum consumption of **150-200 gr/m²**.
- ✓ **As water/humidity barrier** – Apply with roller in three coats with total consumption of **500-600 gr/m²**.
- ✓ Recoat time cannot be determined in terms of hours since it is highly dependent on weather conditions: It can be as low as 2 hours during summer and as high as 24 hours during winter. Use the following rule of thumb to determine when recoating should take place. Recoat (with **AQUASMART®-DUR** or **HYPERDESMO®**) when material has hardened to the degree where it can no longer be punctured by finger nail.

AQUASMART®-DUR

Product Data Sheet

- ✓ Do not exceed the stated consumption numbers, as this will affect adversely its adhesion and durability.
- ✓ Pot life of mixture is 1-hour maximum at 25°C.
- ✓ Do not apply when temperature is below 12°C.
- ✓ Hot concrete should be wetted before application.

Consumption

- As primer – Apply in one or two thin coats with total consumption of **150-200 gr/m²**.
- As water/humidity barrier – Apply in three coats with total consumption of **500-600 gr/m²**.

Cleaning

Clean tools and equipment first with paper and then using water. Under no circumstances should they be re-used to mix/apply polyurethane products.

Shelf Life

Can be kept for 12 months minimum in the original unopened pails in dry places and at temperatures of 5-25°C. Once opened, use as soon as possible.

Packaging

- Component A : 1 Lt, 4 Lt
- Component B : 1 Lt, 4 Lt

Safety Information

AQUASMART®-DUR is free of solvents. Nevertheless, you are advised to observe the standard safety rules: Apply in well-ventilated, no smoking areas, away from naked flames. In closed spaces use ventilators and carbon active masks. The M.S.D.S. (Material Safety Data Sheet) is available on request.

Technical Specifications

In Liquid Form (Before application, After mixing):

Component A – Milky white

Component B – Yellow

Property	Units	Method	Specification
Viscosity (Brookfield) of mixed product	cP	ASTM D2196-86, @ 25 °C	50-100
Specific weight	gr/cm ³	ASTMD1475/DIN53217/ISO2811,@20°C	1.0
Mixing ratio	A:B, by Volume	-	1:1
Tack free time, @ 25 °C & 55% RH	hours	-	3-5
Full cure	days	-	3
Recoat time	-	-	When material has hardened to the degree where it can no longer be punctured by finger nail
Pot life	hours	-	1 @ 25°C

In Cured Form (After application):

Property	Units	Method	Specification
Service temperature	°C	-	10-40
Adhesion to concrete	N/mm ²	ASTM D4541	> 3
Resistance to friction	Gr	ASTM D4541 (Taber 503, CS17, 1.0 kg, 1,000 revs.)	120 * 10 ⁻³

For more information on Hyperdesmo, Hyperseal & Aquasmart range of products and application methods
Please contact Alchimica Technical Service at info@globalbusinessbd.com

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

Global Business Solution

198-202, Nawabpur Tower, Room
No#311, Nawabpur Road, Bangladesh.
Headquarters

7, Lampsakou St,
115 28 Athens, Greece.

R&D / Plant

13, Oryzomylon St,
122 44 Aegaleo, Greece.

CE 25 YEARS
EXPECTED
WORKING LIFE



www.globalbusinessbd.com

Ref: AQUASmart®- DUR /EE/10-06-2019