

## HYPERDESMO®-ADY 810

## Product Data Sheet

### One component, UV resistant, High Traffic / Vehicular Traffic Waterproofing Coating

#### Description

**HYPERDESMO®-ADY 810** is a fully aliphatic, one component, polyurethane liquid membrane designed for use as a top coat for traffic deck coating systems.

The system Build up is :

- Primer (please contact technical service department for primer selection).
- Main waterproofing coating: **HYPERDESMO® CLASSIC**
- Top coat : **HYPERDESMO® ADY 810**

Alternatively it may also be used in a single layer application acting simultaneously as main membrane and top coat. **HYPERDESMO®-ADY 810** is moisture curing, but due to its curing mechanism will provide a bubble and defect free membrane. It has excellent adhesion to **HYPERDESMO®-CLASSIC**, outstanding abrasion and scratch resistance, chemical and hydrolysis resistance. The UV resistance is excellent and the color stability is secure whatever the color. **HYPERDESMO®-ADY 810** is self-leveling, with a good viscosity profile over a large temperature range that will cure to form a bubble free membrane that is recommended to be applied in only one coat.

#### Recommended For

- Top-coating **HYPERDESMO®** on traffic deck systems.
- Top-coating **HYPERDESMO®** on roofs.
- Top-coating **HYPERDESMO-POLYUREA-HC**.
- Top-coating on light roofing from metal or fibrous cement.
- Main membrane and topcoat application in one single layer (on concrete/steel reinforced concrete or otherwise, on other substrates suitable for **HYPERDESMO®** application).

#### Features & Benefits

- Excellent abrasion, impact and UV resistance,
- Excellent mechanical properties, high elasticity, tensile and tear strength.
- Excellent chemical and hydrolysis resistance.

#### Application Procedure

Clean the surface using a high-pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes, etc. must be removed. Further primer information available on request. The application surface must be **dry**.

If used as a top coat , it must be applied within 24-72 hours of **HYPERDESMO®** application, depending on weather conditions.

- ✓ **Priming:** If used as main membrane, apply the required primer as per the **Primer Selection Table**.
- ✓ **Mixing:** Use a low speed (300 rpm) mixer.
- ✓ **Application:** By brush, roller or airless spraying. If applied in sequel layers, do not exceed 48 hours between coats.

#### Compliance

**HYPERDESMO®-ADY 810** is **CE certified** as part of the **HYPERDESMO®** System, offering increased UV resistance and colour protection & traffic resistance.

#### Cleaning

Clean tools and equipment first with paper towels and then using **SOLVENT-01**. Rollers will not be re-usable.

#### Consumption

Minimum total consumption: **±0.5 kg/m<sup>2</sup>**.

#### Packaging

- 1 kg, 6 kg, 15 kg & 25 kg pails.

## HYPERDESMO®-ADY 810

## Product Data Sheet



### Safety Information

Contains volatile flammable solvents. Apply in well-ventilated, no smoking areas, away from naked flames. In closed spaces use ventilators and carbon active masks. Keep in mind that solvents are heavier than air so they creep on the floor. The MSDS (Material Safety Data Sheet) is available on request.



### Shelf Life

Can be kept for minimum 12 months in the original unopened pails in dry places and at temperatures of 5-25°C. Once a pail has been opened, use as soon as possible.



### Technical Specifications

In Liquid Form (Before application):

Property	Units	Method	Specification
Viscosity (Brookfield)	cP	ASTM D2196-86, @ 25°C	4000-6000
Specific weight	gr/cm <sup>3</sup>	ASTM D1475 / DIN 53217 / ISO 2811, @ 20 °C	1.3-1.4
Tack free time, @ 77°F (25°C) & 55% RH	hours	-	6-12
Recoat time	hours	-	24

In Cured Form (After application):

Property	Units	Method	Specification
Service temperature	°C	-	-40 to 90
Max. temperature short time (shock)	°C	-	200
Hardness	Shore A	ASTM D2240/DIN 53505 / ISO R868	95-100
Tensile strength at break @ 23°C	N/mm <sup>2</sup>	ASTM D412/ EN-ISO-527-3	> 19
Percent elongation @ 23°C	%	ASTM D412/ EN-ISO-527-3	> 300
Abrasion Resistance	Mg loss	ASTM D6040, CS17 WHEELS, 1000 REVS, 1000 GR	< 10
Thermal resistance (100 days @ 80°C)	-	EOTA TR011	Passed
QUV Accelerated Weathering Test	-	ASTM G53	Passed (2000 hours)

For more information on Hyperdesmo, Aquasmart & Hyperseal range of products and application methods

Please contact Alchimica Technical Service at [info@globalbusinessbd.com](mailto:info@globalbusinessbd.com)

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

#### Global Business Solution

198-202, Nawabpur Tower, Room No# 311, Nawabpur Road,  
Nawabpur, Dhaka- 1100, Bangladesh.

#### Headquarters

7, Lampsakou St,  
115 28 Athens, Greece.

#### R&D / Plant

13, Oryzomylon St,  
122 44 Aegaleo, Greece.

**CE** 25 YEARS  
EXPECTED  
WORKING LIFE

