

HYPERDESMO® (CLASSIC VERSION)

Product Data Sheet

**Polyurethane Liquid Membrane For Waterproofing & Protection,
Easy Application.** **Description**

HYPERDESMO® (CLASSIC VERSION) is the industry standard in waterproofing. For over 30 years, it has provided a simple solution for waterproofing and protection. It is a one component, low viscosity, polyurethane fluid that cures with the humidity in the atmosphere to produce a highly elastic membrane with strong adhesion to many types of surfaces.

It is based on pure elastomeric hydrophobic polyurethane resin plus special inorganic fillers, which result in excellent mechanical, chemical, thermal, UV and natural element resistance properties.

 **Recommended For**

Waterproofing and protection of:

- Gypsum and cement boards,
- Tiles (under),
- Bathrooms,
- Roofs,
- Light roofing made of metal or fibrous cement,
- Asphalt membranes,
- As the main waterproofing membrane in car park waterproofing systems.

 **Compliance**

- CE: ETA-04/0082.
- BBA: Agrément Certificate 18/5567 (see table below)
- ASTM C 836-95

 **Features & Benefits**

- No thinning is required but SOLVENT-01 may be used.
- Excellent weather and UV resistance. The white colour reflects much of the solar energy and so reduces the internal temperature of buildings considerably.
- Excellent thermal resistance, the product never turns soft. Max service temperature 90°C, max shock temperature 200°C.
- Resistance in the cold: The film remains elastic even down to -40°C.
- Excellent mechanical properties.
- Good chemical resistance.
- Non-toxic after full cure.
- Water vapor transmission: The film breathes so there is no accumulation of humidity under the coat.

 **Limitations**

Not recommended for:

- Unsound substrates (in some cases, application is possible with the use of geotextile reinforcement; please contact our technical department for consultations).
- waterproofing of swimming pool surfaces in contact with chemically treated water.
- ☑ When used in dark colours for exposed use, a protective topcoat of **HYPERDESMO®-ADY-E** (always pigmented at the desired colour) or **HYPERDESMO®-ADY 500** is required.
- ☑ In order to maintain long-term solar reflectance and better colour protection, it is beneficial to apply the aforementioned topcoat layers even when **HYPERDESMO® CLASSIC** is applied in light colours.

HYPERDESMO® (CLASSIC VERSION)

Product Data Sheet

Application Prerequisites

Can be successfully applied on:

Concrete/steel reinforced concrete or otherwise, fibrous cement, mosaic, cement roof tiles, old (but well adhered) acrylic and asphalt coats, wood, corroded metal, and galvanized steel. For information about other substrates, please contact our tech department.

Concrete substrate conditions (standard):

- Hardness: $R_{28} = 15\text{Mpa}$.
- Humidity: $W < 10\%$.
- Temperature: $5\text{-}35^{\circ}\text{C}$.
- Relative humidity: $< 85\%$

Primer selection for special conditions and substrates: Please refer to the **Primer Selection Table**.

Application Procedure

Clean the surface using a high-pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes must be removed. Fill surface irregularities with appropriate products.

- ✓ **Priming:** Apply the required primer following the guidelines above.
- ✓ **Mixing:** Use a low speed (300 rpm) mixer. May optionally be thinned with 5-10% SOLVENT-01. For application by spraying (airless) thin with 10% SOLVENT-01.
- ✓ **Application:** Apply the material with roller or brush in two, at least, coats. Leave 6-24 hours between coats. If more time passes (for example more than 4 days) or if you are unsure of the interlayer adhesion please contact our technical service department.

Precautions

Contains volatile flammable solvents. Apply in well-ventilated, no smoking areas, away from naked flames. In closed spaces use ventilators and carbon active masks. Keep in mind that solvents are heavier than air so they creep on the floor. The MSDS (Material Safety Data Sheet) is available on request.

Consumption

First coat: **0.75-0.9 kg/m²**.
 Second coat: **0.75-0.9 kg/m²**.
 Minimum total consumption: **1.5-1.8 kg/m²**.

Shelf Life

Can be kept for minimum 12 months in the original unopened pails in dry places and at temperatures of 5-25 °C. Once a pail has been opened, use as soon as possible.

Cleaning

Clean tools and equipment first with paper towels and then using SOLVENT-01. Rollers will not be re-usable.

Packaging

1 kg, 6 kg, 15 kg & 25 kg.

HYPERDESMO® (CLASSIC VERSION)

Product Data Sheet

Classification According To EOTA (European Organisation Of Technical Approval) & BBA (British Board Of Agrément)

REQUIREMENT	HYPERDESMO®	HYPERDESMO® + HYPERDESMO®-ADY
Minimum expected working life	W3 (25 years)	W2 (10 years)
Climatic zone	S (Severe)	
User load	P1	P3
Roof slope	S1 - S4	
Minimum surface temperature	TL3 (-20 °C)	
Maximum surface temperature	TH4 (90 °C)	
Exposure to external fire	Broof (t1,t4)	
Reaction to fire	Class E	


Technical Specifications

The product in liquid form (before application):

Property	Units	Method	Specification
Viscosity (BROOKFIELD)	cP	ASTM D2196-86, @ 25 °C	3000-6000
Specific weight	gr/cm ³	ASTM D1475 / DIN 53217 / ISO 2811, @ 20°C	1.35-1.45
Flash point	°C	ASTM D93, closed cup	42
Tack free time, @ 25°C & 55% RH	hours	-	4
Recoat time	hours	-	6-24

The cured membrane:

Property	Units	Method	Specification
Service temperature	°C	-	-40 to 90
Max. temperature short time (shock)	°C	-	200
Hardness	Shore A	ASTM D2240 / DIN 53505 / ISO R868	60
Tensile strength at break @ 23 °C	N/mm ²	ASTM D412 / EN-ISO-527-3	>8
Percent elongation @ 23 °C	%	ASTM D412 / EN-ISO-527-3	> 500
Water vapor transmission	gr/m ² .hr	ASTM E96 (Water Method)	0.8

HYPERDESMO® (CLASSIC VERSION)

Product Data Sheet

Adhesion to concrete	N/mm ²	ASTM D4541	> 2
Hydrolysis (8% KOH, 15 days @ 50°C)	-	-	no significant elastomeric property change
Hydrolysis (H ₂ O, 14-day cycle RT-100 °C)	-	-	no significant elastomeric property change
Hydrolysis (H ₂ O, 30-day cycle 60-100 °C)	-	-	no significant elastomeric property change
HCL (PH=2, 10 days @ RT)	-	-	no significant elastomeric property change
Thermal resistance (100 days @ 80 °C)	-	EOTA TR011	passed
QUV Accelerated Weathering Test	-	ASTM G53	passed (2000 hours)

For more information on Hyperdesmo, Hyperseal & Aquasmart range of products and application methods

Please contact Alchimica Technical Service at info@globalbusinessbd.com

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

Global Business Solution

198-202, Nawabpur Tower, Room No# 311, Nawabpur Road, Nawabpur, Dhaka- 1100, Bangladesh.

Headquarters

7, Lampsakou St,
115 28 Athens, Greece.

R&D / Plant

13, Oryzomylon St,
122 44 Aegaleo, Greece.

CE 25 YEARS
EXPECTED
WORKING LIFE

