



TOPSEAL

Polymer Modified Bitumen Membrane with Non-woven Polyester

BITUMAT TOPSEAL is a finely formulated polymer modified bitumen membrane designed for economical and easy applications.

BITUMAT TOPSEAL waterproofing membrane consists of non-woven polyester reinforcement, impregnated and coated on both sides with polymer modified bitumen.

USES

BITUMAT TOPSEAL membrane is ideal for a wide range of waterproofing applications including roofs, car parks, reservoirs, etc.

OUTSTANDING FEATURES

- Excellent cost performance ratio
- Easy to install
- Total Impermeability
- Good bondability & seam integrity
- Stability at high temperature
- Good flexibility
- Compatible with all normal roofing and building components

GENERAL DATA

Nominal Roll Length : 10 Mtrs.
 Nominal Roll Width : 1 Mtr.
 Nominal Thickness : 3,4,5 MM
 Nominal Weight : 4mm / 47 Kgs per Roll
 Re-inforcement : Non-woven polyester

PACKAGING

- 3mm - 28 Rolls / Pallet
- 4mm - 23 Rolls / Pallet

FINISHES

BITUMAT TOPSEAL is available in two basic finishes :

- Black smooth finish with polyethylene surfaces for covered applications.
- Granule surfacing for exposed applications.

QUALITY CONTROL

In addition to stringent regular tests by BITUMAT laboratory, our products are tested periodically by Independent laboratories.

INSTALLATION TOOLS REQUIRED

Gas torch, Knife, Trowel, Measuring tape, Marking string, Gloves

APPLICATION

BITUMAT TOPSEAL is installed by torch welding method, loose-laid or fully bonded to substrate. When loose-laid, only laps are bonded together.

Peripheries and protrusions are sealed according to specifications.

COVERAGE RATE (Approx.)

(Rate may vary as per site requirement)

Flat areas : 1.15 M²/M² per layer
 with 10 cms. side laps
 and 15 cms. end laps.
 Base flashing : 100x35 cms. with 15
 cm. end laps, 0.40 M²/
 Linear Mtr.

Average wastage : 3 - 5 %

TORCHING GUIDELINES

The underside of the membrane should be torched just enough to superficially melt the bitumen. Excessive heating may damage the reinforcement. Overlaps should be re-heated from the top and resealed with a trowel to ensure seam integrity.

For details of installation methods and flashing requirements, consult the Bitumat technical department.

BITUMAT
بيتومات

The Power to Perform

قوة في الأداء



NRCA MEMBER



ISO CERTIFIED



BITUMAT
بيتومات

TOPSEAL

Polymer Modified Bitumen Membrane with
Non-woven Polyester

Technical Data

PMB02 30-Q R-00 00

No.	Property	Typical Value	Test Method
1.	Reinforcement	Non-woven Polyester	---
2.	Softening Point °C	150	ASTM D 36
3.	Penetration @ 25 °C dmm	18	ASTM D 5
4.	Tensile Strength, L/T, N/5 CM @23 ±2 °C	600 / 400	ASTM D 5147
5.	Elongation, L/T, % @23 ±2 °C	40 / 45	ASTM D 5147
6.	Tear Strength, L/T, N	300 / 200	ASTM D 5147
7.	Heat Resistance, @ 80 °C	No flow	ASTM D 5147
8.	Cold Flexibility, °C	0 to +5	ASTM D 5147
9.	Lap Joint Strength L/T, N/5 CM @23 ±2 °C	620 / 400	CGSB 37 GP 56 M

The information given in this Technical Data Sheet reflects typical median properties based on laboratory test, and practical experience; subject to the tolerance levels of UEAtc directives. However, as the product is often used under conditions beyond our control, we can't warrant but the product itself.

THIS PUBLICATION AUTOMATICALLY SUPERSEDES ALL PREVIOUS PUBLICATIONS RELATING TO THIS PRODUCT.

Our Agent:

GLOBAL BUSINESS SOLUTION

Room No: 311, Nawabpur Tower Market

198-202, Nawabpur Road, Dhaka Bangladesh

T: + 8802 57164405 (Dk) 880312854796 (Chittagong)

M: 8801916822106, email: wahidgbs@gmail.com

BITUMAT COMPANY LIMITED

Corporate Office : P.O. Box 7487, Dammam 31462, Kingdom of Saudi Arabia Tel. No. (966-3) 8121210 / 8121213 Fax No: (966-3) 8121190

Central Region : P.O. Box 58698, Riyadh 11515, Kingdom of Saudi Arabia Tel. No. (966-1) 4770443 / 4792553 Fax No: (966-1) 4762318

Western Region : P.O. Box 12605, Jeddah 21483, Kingdom of Saudi Arabia Tel. No. (966-2) 6544449 Fax No: (966-2) 6640506

Email : marketing@bitumat.com / Website: www.bitumat.com



NRCA MEMBER



ISO CERTIFIED

The Power to Develop

قيادة في الأداء