



TEST REPORT

1. NO : CT25-001728E
2. Client
 - Name : DAEHWA PRECISION Co.,Ltd
 - Address : B110, 474, Dunchon-daero, Jungwon-gu, Seongnam-si, Gyeonggi-do, Korea
3. Date of Test : 2025.01.03 ~ 2025.03.17
4. Use of Report : Source for approval
5. Test Sample : DHP-2000 Rigid Polyurethane Foam
6. Test Method
 - (1) ASTM D 1084-16
 - (2) ASTM D1002-10
 - (3) ASTM D 1475-13

7. Test Results

1) DHP-2000 Rigid Polyurethane Foam

| Test Item(s) | Unit | Test Method | Test Results | Remark | Loc. |
|---|-------|-------------|--------------|--------------------------------|------|
| Viscosity | mPa·s | (1) | 300 | (23 ± 2) °C (50 ± 5) % R.H. | A |
| Shear strength by tensile loading | N/mm | (2) | 2 | | |
| Specific gravity (Specific gravity cup method) | - | (3) | 1.13 | | |

- * Compounding Ratio(Weight Ratio) - [One solution type]
- * BROOKFIELD VISICOSIMETER[Spindle LV-2, 20 r/min, 23 °C]
- * Location

A : 73, Yangcheong 3-gil, Ochang-eup, Cheongwon-Gu, Cheongju-Si, Chungbuk, Korea

----- End of Report -----

| | | | | |
|-------------|------------------------|--|-----------------------|--|
| Affirmation | Tested By | | Technical Manager | |
| | Name : Kim Kyoung Hoon | | Name : Lee, Bong Chun | |

This report is not accredited by KOLAS and KS Q ISO/IEC 17025.
 Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).

2025.03.17

Korea Conformity Laboratories



Result Inquiry : 73, Yangcheong 3-gil, Ochang-eup, Cheongwon-Gu, Cheongju-Si, Chungbuk, Korea (82-43-210-8982)

