



# TEST REPORT

1. NO : CT25-001717E
2. Client
  - Name : DAEHWA PRECISION Co.,Ltd
  - Address : B110, 474, Dunchon-daero, Jungwon-gu, Seongnam-si, Gyeonggi-do, Korea
3. Date of Test : 2025.01.03 ~ 2025.03.17
4. Use of Report : Source for approval
5. Test Sample : DH-200 Low Viscosity
6. Test Method
  - (1) KS F 4923:2022
  - (2) KS M 3015:2003
  - (3) KS F 2760:2018






Affirmation	Tested By Name : Kim Kyoung Hoon		Technical Manager Name : Lee, Bong Chun	
This report is not accredited by KOLAS and KS Q ISO/IEC 17025. Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).				

2025.03.17

Korea Conformity Laboratories



Result Inquiry : 73, Yangcheong 3-gil, Ochang-eup, Cheongwon-Gu, Cheongju-Si, Chungbuk, Korea (82-43-210-8982)



# TEST REPORT

No : CT25-001717E

## 7. Test Results

### 1) DH-200 Low Viscosity

Test Item(s)	Unit	Test Method	Test Results	Remark	Loc.
Hardening Shrinkage Rate - Standard Condition	%	(1)	1	(25 ± 2) °C (50 ± 5) % R.H.	A
Tensile Strength - Standard Condition	N/mm <sup>2</sup>	(1)	23.5		
Elongation Rate - Standard Condition	%	(1)	1		
Bond Strength - Standard Condition	N/mm <sup>2</sup>	(1)	7.3		
Heat Changes - Mass Rate of Change	%	(1)	1		
Heat Changes - Volume Rate of Change	%	(1)	2		
Viscous - Viscosity	mPa·s	(1)	234		
Compressive Strength	N/mm <sup>2</sup>	(2)	55	(20 ± 2) °C (65 ± 20) % R.H.	
Slant Shear Strength - Standard Condition	MPa	(3)	12.6		

\* Compounding Ratio(Weight Ratio) - [Resin : Hardener = 2 : 1]

\* BROOKFIELD Visicosimeter [Spindle LV-2, 20 r/min, 23 °C]

\* Location

A : 73, Yangcheong 3-gil, Ochang-eup, Cheongwon-Gu, Cheongju-Si, Chungbuk, Korea

----- End of Report -----

